

Technical Data Sheet

Graphene Thermal Management Coating I-HS41

I-HS41 is a solvent based graphene coating designed for thermal management and heat dissipation systems. The coating can be easily sprayed and the coating layer shows excellent heat dissipation ability.

Physical Property

- Appearance : Black
- Resin : Epoxy
- Solid content: 56±2 %
- Viscosity: 150±50 cps (ABC mixture)
- Shelf Life : Sealed for 6 months @ 25 °C
- Usage for coating : ~ 10 m²/kg*

⁺ Viscosity: Brookfield HADV-I+ with Spindle #2 @ 30rpm

*Estimation based on plane structure and no guaranteed for irregular shape structure.

Recommended Operation Condition

- Settling of solid may occur and compositions should be thoroughly mixed prior to use.
- Mix carefully in case of bubbling during operation.
- I-HS41_A: Main Coating; I-HS41_B: Hardener; I-HS41_C: Thinner
- Optimum A: B: Thinner = 5:1:3 with pot life of 8 hours.
- Recommended coating method : Spray coating
- Surface of substrate should be clean without any surface treatment.
- Recommended thickness : 30~50 μm of dried film

The information about products in this document provides an orientation and qualities. The data are controlled periodically by assurance system. No warranty, guarantee, representation, or legal binding is offered.

Signature is unnecessary in this computer-generated document



Please note that partial of the analysis data are also conveniently available online at www.graphene.com.tw

- Curing condition : 60 min @ 100 °C
- Thinner of I-HS41 is designated and contact Enerage Inc. for more information.
- Clean up : Acetone and MEK
- Please wear protective cloths as well as installing full ventilation during the operation.

Storage

- Graphene paint should be stored in a clean, stable environment at room temperature with their lids tightly sealed.
- Storage in high temperature (>30 °C) or freezers (<0 °C) is NOT recommended.

Safety Issue

- Products are intended for use in an industrial environment by trained personnel. Please follow proper health/safety processes regarding storage, handling and processing of the products. For Safety and Handling information pertaining to this product, refer to Safety Data Sheet (SDS).

Package

- The standard package is 3KG. The main coating (I-HS41-A), hardener (I-HS41-B) and thinner (I-HS41-C) are packaged separately. It could be customized according to customers' requirement.

The information about products in this document provides an orientation and qualities. The data are controlled periodically by assurance system. No warranty, guarantee, representation, or legal binding is offered.

Signature is unnecessary in this computer-generated document

Please note that partial of the analysis data are also conveniently available online at www.graphene.com.tw



The information about products in this document provides an orientation and qualities. The data are controlled periodically by assurance system. No warranty, guarantee, representation, or legal binding is offered.

Signature is unnecessary in this computer-generated document

Tel : +886-3-990-2100 Fax+886-3-990-2500
No.5, Ligong 3rd Rd., Wujie Township, Yilan County 26841, Taiwan, R.O.C.

