

Technical Data Sheet

Graphene Lubricant Additive C-SI10

C-SI10 is a concentrated graphene silane dispersion (2 wt%) used as an additive in lubricant. The additive can be easily diluted and blended into the lubricant such as engine oil with high uniformity.

Physical Property

- Appearance: Black liquid
- Solid Content: 2 ± 0.1 wt%
- Solvent: Hexadecyltrimethoxysilane
- Viscosity⁺: $1,000\pm 500$ cps
- Shelf Life: Sealed for 3 months @ 25 °C

⁺ Viscosity: Brookfield HADV-I+ with Spindle #3 @ 50rpm

Recommended Operation Condition

- Dilute the C-SI10 with lubricant before using; 10 ppm graphene in the lubricant is recommended. (For example: 0.5 g C-SI10 added into 1 L engine oil.)
- Settling of solid may occur and compositions should be thoroughly mixed prior to use.
- Please wear protective cloths as well as installing full ventilation during the operation.

The information about products in this document provides an orientation and qualities. The data are controlled periodically by assurance system. No warranty, guarantee, representation, or legal binding is offered.

Signature is unnecessary in this computer-generated document

Please note that partial of the analysis data are also conveniently available online at www.graphene.com.tw

Storage

- Graphene lubricant additive should be stored in a clean and stable dry box at room temperature with their lids tightly sealed.
- Storage in high temperature ($>30\text{ }^{\circ}\text{C}$) or freezers ($<0\text{ }^{\circ}\text{C}$) is NOT recommended.

Safety Issue

- Products are intended for use in an industrial environment by trained personnel. Please follow proper health/safety processes regarding storage, handling and processing of the products. For Safety and Handling information pertaining to this product, refer to Safety Data Sheet (SDS).

Package

- The standard package is 100 g/Plastic jar. It could be customized according to customers' requirement.



The information about products in this document provides an orientation and qualities. The data are controlled periodically by assurance system. No warranty, guarantee, representation, or legal binding is offered.

Signature is unnecessary in this computer-generated document